

TECHNICAL DATA SHEET

Edition: 2

Tensional steel strapping produced acc. to EN 13246

| | |
|--------------------|------------------------|
| PRODUCT | STEEL STRAPPING |
| DIMENSION | 13 x 0.40 |
| QUALITY | Standard |
| Article No. | 0613040 |

| Mechanical Properties | |
|------------------------------------|---|
| Width | 12.7 ± 0.15 mm |
| Thickness | 0.40 ± 0.03 mm |
| Tensile Strength | min 800 N/mm ² average 920 N/mm ² |
| Break Load | min 4060 N average 4670 N |
| Elongation, A₅ | average 6.0 % |
| Elongation, A₁₀₀ | min 0.5 % average 2.0 % |
| Surface Finish | black painted and waxed, deburred edges |

Tensile testing acc. to ISO 6892-1

| Packaging Conditions | |
|-----------------------------|--------------------------------|
| Winding | oscillated |
| ID | 406 mm |
| OD | 600 mm ca. |
| Coil weight | 50 kg ca. |
| Coils per pallet | 12 |
| Pallet weight | 600 kg ca. |
| Pallet dimension | 675 x 580 x 130 (W x L x H) mm |
| External protection | cardboard cover |

COMPANY WITH
 MANAGEMENT SYSTEM
 CERTIFIED BY DNV
 = ISO 9001 =
 = ISO 14001 =

BURSERYDS BRUK AB

Storg. 15-17, SE-330 26 Burseryd, Sweden

Tel. +46 371 37500, Fax. +46 371 37519

 Email info@burserydsbruk.se, Web-site www.burserydsbruk.se

Reg. No. 556247-4204

TECHNICAL DATA SHEET

Edition: 2

Tensional steel strapping produced acc. to EN 13246

| | |
|--------------------|------------------------|
| PRODUCT | STEEL STRAPPING |
| DIMENSION | 13 x 0.50 |
| QUALITY | Standard |
| Article No. | 0613050 |

| Mechanical Properties | |
|------------------------------------|---|
| Width | 12.7 ± 0.15 mm |
| Thickness | 0.50 ± 0.03 mm |
| Tensile Strength | min 800 N/mm ² average 900 N/mm ² |
| Break Load | min 5080 N average 5710 N |
| Elongation, A₅ | average 7.0 % |
| Elongation, A₁₀₀ | min 1.0 % average 2.5 % |
| Surface Finish | black painted and waxed, deburred edges |

Tensile testing acc. to ISO 6892-1

| Packaging Conditions | |
|-----------------------------|--------------------------------|
| Winding | oscillated |
| ID | 406 mm |
| OD | 600 mm ca. |
| Coil weight | 50 kg ca. |
| Coils per pallet | 12 |
| Pallet weight | 600 kg ca. |
| Pallet dimension | 675 x 580 x 130 (W x L x H) mm |
| External protection | cardboard cover |

COMPANY WITH
 MANAGEMENT SYSTEM
 CERTIFIED BY DNV
 = ISO 9001 =
 = ISO 14001 =

TECHNICAL DATA SHEET

Edition: 2

Tensional steel strapping produced acc. to EN 13246

| | |
|--------------------|------------------------|
| PRODUCT | STEEL STRAPPING |
| DIMENSION | 16 x 0.40 |
| QUALITY | Standard |
| Article No. | 0616040 |

| Mechanical Properties | |
|------------------------------------|---|
| Width | 15.9 ± 0.15 mm |
| Thickness | 0.40 ± 0.03 mm |
| Tensile Strength | min 800 N/mm ² average 920 N/mm ² |
| Break Load | min 5090 N average 5850 N |
| Elongation, A₅ | average 6.5 % |
| Elongation, A₁₀₀ | min 0.5 % average 2.0 % |
| Surface Finish | black painted and waxed, deburred edges |

Tensile testing acc. to ISO 6892-1

| Packaging Conditions | |
|-----------------------------|--------------------------------|
| Winding | oscillated |
| ID | 406 mm |
| OD | 600 mm ca. |
| Coil weight | 50 kg ca. |
| Coils per pallet | 12 |
| Pallet weight | 600 kg ca. |
| Pallet dimension | 675 x 580 x 130 (W x L x H) mm |
| External protection | cardboard cover |

COMPANY WITH
 MANAGEMENT SYSTEM
 CERTIFIED BY DNV
 = ISO 9001 =
 = ISO 14001 =

TECHNICAL DATA SHEET

Edition: 2

Tensional steel strapping produced acc. to EN 13246

| | |
|--------------------|------------------------|
| PRODUCT | STEEL STRAPPING |
| DIMENSION | 16 x 0.50 |
| QUALITY | Standard |
| Article No. | 0616050 |

| Mechanical Properties | |
|------------------------------------|---|
| Width | 15.9 ± 0.15 mm |
| Thickness | 0.50 ± 0.03 mm |
| Tensile Strength | min 800 N/mm ² average 900 N/mm ² |
| Break Load | min 6360 N average 7150 N |
| Elongation, A₅ | average 7.0 % |
| Elongation, A₁₀₀ | min 1.0 % average 2.5 % |
| Surface Finish | black painted and waxed, deburred edges |

Tensile testing acc. to ISO 6892-1

| Packaging Conditions | |
|-----------------------------|--------------------------------|
| Winding | oscillated |
| ID | 406 mm |
| OD | 600 mm ca. |
| Coil weight | 50 kg ca. |
| Coils per pallet | 12 |
| Pallet weight | 600 kg ca. |
| Pallet dimension | 675 x 580 x 130 (W x L x H) mm |
| External protection | cardboard cover |

COMPANY WITH
 MANAGEMENT SYSTEM
 CERTIFIED BY DNV
 = ISO 9001 =
 = ISO 14001 =

TECHNICAL DATA SHEET

Edition: 2

Tensional steel strapping produced acc. to EN 13246

| | |
|--------------------|------------------------|
| PRODUCT | STEEL STRAPPING |
| DIMENSION | 19 x 0.50 |
| QUALITY | Standard |
| Article No. | 0619050 |

| Mechanical Properties | |
|------------------------------------|---|
| Width | 19.0 ± 0.20 mm |
| Thickness | 0.50 ± 0.03 mm |
| Tensile Strength | min 800 N/mm ² average 900 N/mm ² |
| Break Load | min 7600 N average 8550 N |
| Elongation, A₅ | average 7.5 % |
| Elongation, A₁₀₀ | min 1.0 % average 2.5 % |
| Surface Finish | black painted and waxed, deburred edges |

Tensile testing acc. to ISO 6892-1

| Packaging Conditions | |
|-----------------------------|--------------------------------|
| Winding | oscillated |
| ID | 406 mm |
| OD | 600 mm ca. |
| Coil weight | 50 kg ca. |
| Coils per pallet | 12 |
| Pallet weight | 600 kg ca. |
| Pallet dimension | 675 x 580 x 130 (W x L x H) mm |
| External protection | cardboard cover |

COMPANY WITH
 MANAGEMENT SYSTEM
 CERTIFIED BY DNV
 = ISO 9001 =
 = ISO 14001 =

BURSERYDS BRUK AB

Storg. 15-17, SE-330 26 Burseryd, Sweden

Tel. +46 371 37500, Fax. +46 371 37519

 Email info@burserydsbruk.se, Web-site www.burserydsbruk.se

Reg. No. 556247-4204

TECHNICAL DATA SHEET

Edition: 2

Tensional steel strapping produced acc. to EN 13246

| | |
|--------------------|------------------------|
| PRODUCT | STEEL STRAPPING |
| DIMENSION | 19 x 0.70 |
| QUALITY | Standard |
| Article No. | 0619070 |

| Mechanical Properties | |
|------------------------------------|---|
| Width | 19.0 ± 0.20 mm |
| Thickness | 0.70 ± 0.04 mm |
| Tensile Strength | min 800 N/mm ² average 850 N/mm ² |
| Break Load | min 10640 N average 11300 N |
| Elongation, A₅ | average 7.5 % |
| Elongation, A₁₀₀ | min 1.0 % average 3.0 % |
| Surface Finish | black painted and waxed, deburred edges |

Tensile testing acc. to ISO 6892-1

| Packaging Conditions | |
|-----------------------------|--------------------------------|
| Winding | oscillated |
| ID | 406 mm |
| OD | 600 mm ca. |
| Coil weight | 50 kg ca. |
| Coils per pallet | 12 |
| Pallet weight | 600 kg ca. |
| Pallet dimension | 675 x 580 x 130 (W x L x H) mm |
| External protection | cardboard cover |

COMPANY WITH
 MANAGEMENT SYSTEM
 CERTIFIED BY DNV
 = ISO 9001 =
 = ISO 14001 =

TECHNICAL DATA SHEET

Edition: 2

Tensional steel strapping produced acc. to EN 13246

| | |
|--------------------|------------------------|
| PRODUCT | STEEL STRAPPING |
| DIMENSION | 32 x 0.80 |
| QUALITY | Standard |
| Article No. | 0732080 |

| Mechanical Properties | |
|------------------------------------|---|
| Width | 31.8 ± 0.20 mm |
| Thickness | 0.80 ± 0.04 mm |
| Tensile Strength | min 750 N/mm ² average 830 N/mm ² |
| Break Load | min 19080 N average 21110 N |
| Elongation, A₅ | average 8.0 % |
| Elongation, A₁₀₀ | min 2.0 % average 3.5 % |
| Surface Finish | black painted and waxed, deburred edges |

Tensile testing acc. to ISO 6892-1

| Packaging Conditions | |
|-----------------------------|--------------------------------|
| Winding | ribbon |
| ID | 300 mm |
| OD | 600 mm ca. |
| Coil weight | 48 kg ca. |
| Coils per pallet | 13 |
| Pallet weight | 600 kg ca. |
| Pallet dimension | 675 x 580 x 130 (W x L x H) mm |
| External protection | cardboard cover |

COMPANY WITH
 MANAGEMENT SYSTEM
 CERTIFIED BY DNV
 = ISO 9001 =
 = ISO 14001 =

TECHNICAL DATA SHEET

Edition: 2

Tensional steel strapping produced acc. to EN 13246

| | |
|--------------------|------------------------|
| PRODUCT | STEEL STRAPPING |
| DIMENSION | 32 x 1.00 |
| QUALITY | Standard |
| Article No. | 0732100 |

| Mechanical Properties | |
|------------------------------------|---|
| Width | 31.8 ± 0.20 mm |
| Thickness | 1.00 ± 0.04 mm |
| Tensile Strength | min 750 N/mm ² average 790 N/mm ² |
| Break Load | min 23850 N average 25120 N |
| Elongation, A₅ | average 9.0 % |
| Elongation, A₁₀₀ | min 2.0 % average 4.0 % |
| Surface Finish | black painted and waxed, deburred edges |

Tensile testing acc. to ISO 6892-1

| Packaging Conditions | |
|-----------------------------|--------------------------------|
| Winding | ribbon |
| ID | 300 mm |
| OD | 600 mm ca. |
| Coil weight | 48 kg ca. |
| Coils per pallet | 13 |
| Pallet weight | 600 kg ca. |
| Pallet dimension | 675 x 580 x 130 (W x L x H) mm |
| External protection | cardboard cover |

COMPANY WITH
 MANAGEMENT SYSTEM
 CERTIFIED BY DNV
 = ISO 9001 =
 = ISO 14001 =